



CERTIFICATION
FBP-914 BATCH
#19636

PRODUCT	DESCRIPTION	TYPE	METHOD	SENSITIVITY	FORM	CLASS	APPROVAL DATE
FBP-914	Fluorescent Penetrant	I	A & C	4	N/A	N/A	25-MAY-2020

We hereby certify that this batch of inspection material when tested following manufacture meets the following:
Certificamos que este lote de material de inspección cumple con los siguientes requisitos cuando es probado despues de la fabricación:

- Certified to SAE AMS 2644G and on the Qualified Products List (test reference: AFWAL/MLS 86-88).
- ISO/FDIS 3452
- Boeing BSS 7039, BAC 20-20-02
- Rolls-Royce RPS-702-7, RRP 58003C
- NAVSEA 250-1500-1 ¶ 12.5.1.1.1, Rev 17
- AMS-2647F, ASTM E-165/ E165M-16, ASTM E-1417/E1417M-16
- ASME Boiler & Pressure Vessel Code 2017, Section V, Article 6, appendix II-¶-641& II-¶-642
- 10 CFR part 21 applies.

Is free of all known Ozone depleting substances and mercury contamination and was not made in any mercury bearing equipment. Does not contain polychlorinated biphenyl (PCB), nonylphenol ethoxylates (NPE), or RoHS banned substances.
Esta libre de todas sustancias degradantes del ozono, de contaminación de mercurio, y no fue fabricado usando equipo conteniendo mercurio. No contiene polychlorinated biphenyl (PCB), nonylphenol ethoxylates (NPE), o RoHS sustancias prohibidas.

- Warranty shelf life is 5 years from date of batch approval.
Vida útil de garantía son 5 años desde la fecha del "approval date".
- Batch number is on bulk labels or bottom of aerosol cans.
Numeros de lote se encuentran en las etiquetas de los botes a granel o en el fondo de los botes de aerosol.

PO# _____

QUALITY ASSURANCE TESTS	REQUIREMENTS	BATCH RESULTS
Appearance:	Clear green liquid, no sediment.	PASS
Density:	958 g/L - 990 g/L @ 21.1°C (70°F)	966 g/L
Flash Point: AMS-2644G ¶ 3.3.3; ASTM D-93	> 93.3°C (> 200 °F)	> 200°F
Viscosity: ASTM D-445, AMS-2644G ¶ 3.3.4	24.4 - 29.8 mm ² /s @ 37.7°C (100°F)	24.9 mm ² /s
Fluorescent Brightness: AMS-2644G ¶ 3.3.8.3.3; per ASTM E-1135-19	≥ 95 % of level 4 std. FP-4PE	133.2%
Water Tolerance AMS-2644G ¶ 3.3.8.5	≥ 5 %	19.0%
Removability: AMS-2644G ¶ 3.3.8.6	Equal to MLC Level 4 Standard	PASS
Water Content, ASTM E-1417/E1417M-16 annex A1 (Karl Fischer)	< 1 %	0.4%
Sulfur Content: per ASTM E-165/E165M-18 ¶ 9.1.2 Annex A4	≤ 200 ppm (0.02 %)	< 200 ppm
Chloride Content: ASTM E-165/E165M-18 ¶ 9.1.2 Annex A4	≤ 200 ppm (0.02 %)	< 200 ppm
Total Halogen Content: ASTM E-165/E165M-18 ¶ 9.1.2 Annex A4	≤ 200 ppm (0.02 %)	< 200 ppm

MET-L-CHEK QUALITY ASSURANCE

BATCH TESTED BY:

Rick Valdez

RICK VALDEZ
LAB TECHNICIAN

BATCH APPROVED BY:

Peter Pelayo

PETER PELAYO
QUALITY MANAGER
ASNT/NAS 410 NDT LEVEL 3

Rev. 8/19



Met-L-Chek Company, 1639 Euclid St. Santa Monica, CA 90404, U.S.A.
P: 310-450-1111 F: 310-452-4046 E: info@met-l-chek.com W: www.met-l-chek.com